

BITUMEN 40/50

	SPECIFICATION	TEST METHOD
Specific Gravity@22/25°C	1.01/1.06	D-70
Penetration @ 25°C	40/50	D-5
Softening Point°C	52/60	D-36
Ductility...25°C	100min	D-113
Loss on Heating(wt)%	0.2max	D-6
Drop in Penetration after Heating%	20max	D-6&D-5
Flash point (approximate) °C	250	D-92
Solubility in CS2(Wt)%	99.5min	D-4
Spot test	Negative	*A.A.S.H.O.T.102

* American Association of State Highway Officials.