

Bitumen 60/70

	SPECIFICATION	TEST METHOD
Specific Gravity@22/25°C	1.01/1.06	D-70
Penetration @25°C	60/70	D-5
Softening Point°C	49/56	D-36
Ductility...25°C	100min	D-113
Loss on Heating(wt)%	0.2max	D-6
Drop in Penetration after Heating%	20max	D-6&D-5
Flash point (approximate) °C	250	D-92
Solubility in CS ₂ (Wt)%	99.5min	D-4
Spot test	Negative	*A.A.S.H.O.T.102

* American Association of State Highway Officials.