

### CUTBACK BITUMEN MC-250

	SPECIFICATION	TEST METHOD
<b>KINEMATIC VISCOSITY-60oC</b>	<b>Cst. 250-500</b>	<b>D-2170</b>
<b>Flash point (Tag open-cup) °C</b>	<b>66min</b>	<b>D-3143</b>
<b>Distillation test</b>		<b>D-402</b>
<b>Distillate ,Vol% of total distillate to360°C</b>		
<b>to 225°C</b>	<b>(Vol)% 10max</b>	
<b>to 260°C</b>	<b>(Vol)% 15-55</b>	
<b>to 316°C</b>	<b>(Vol)% 60-87</b>	
<b>Reside from distillation</b>		
<b>to 360°C</b>	<b>(Vol)% 67min</b>	
<b>Test on residue from distillation</b>		
<b>Ductility...25°C</b>	<b>Cms. 100min</b>	<b>D-113</b>
<b>Penetration @25°C</b>	<b>120-250</b>	<b>D-5</b>
<b>Solubility in trichloroethylen</b>	<b>(wt)% 99.0 min</b>	<b>D-2042</b>
<b>Water content</b>	<b>(Vol)% 0.2max</b>	<b>D-95</b>