



Melamine Specification Sheet

Licensors : Ninyong (CNCCC)
Applications : Laminates (High Pressure) – (Low Pressure), Adhesive Resins,
Moulding Compounds, Coatings, Dishes

Specification	Range
Melamine Content	WT percent bigger than 99.8 percent
Water Content	WT percent 0.10 max.
PH	7.5min. / 9.5max.
Color (Pt-Co)	20max.
Turbidity	20max.
Size	Percent 80 (80 MESH) min.
H ₂ O Solu.20°C	Clear
Ash Content	WT percent smaller than .003 max.
Hydrophob test	30-70 min max.
Formaldehyde Solubility (Before 10 Min.)	clear